

Kohlearten			Wassergehalt (%)	Energiegehalt af* (kJ/kg)	flüchtige Anteile waf** (%)		
UN-ECE	USA (ASTM)	Deutschland (DIN)					
Peat	Peat	Torf					
Ortho-Lignite	Lignite	WEICHBRAUNKOHLE		75	6,700		
Meta-Lignite		Mattbraunkohle	HARTKOHLE	35	16,500		
Subbitum. Coal	Sub-bituminous Coal	Glanzbraunkohle		25	19,000		
		Flammkohle		10	25,000	45	
Bituminous Coal	High Volatile Bituminous Coal	Gasflammkohle				40	
		Gaskohle				35	
		Fettkohle		Kokskohle 36,000		28	
	Medium Vol. Bitumin. Coal	Eßkohle				19	
	Low Vol. Bitumin. Coal	Magerkohle				14	
Anthracite	Semi-Anthracite			3	36,000	10	
	Anthracite	Anthrazit					

af \* = aschefrei

waf \*\* = wasser- und aschefreie Substanz